


Desso Textile floor covering - Broadloom

Decor B 080 080

Specification according to EN 1307

Type of manufacture	ISO 2424	Woven - Axminster						
Aspect	ISO 2424	Cut pile						
Dye method		Hank dyed						
Width		cm	400	ft	13.1			
Primary backing	ISO 2424	Polypropylene weft / Polyester-based warp						
Secondary backing	ISO 2424	Copolymer						
Pile fibre composition	ISO 2424	80% wool - 20% polyamide						
Total thickness	ISO 1765	mm	10.0	inch	0.4			
Effective pile thickness	ISO 1766	mm	8.0	inch	0.31			
Total mass	ISO 8543	g/m ²	1860	oz/yd ²	54.9			
Total pile mass	ISO 2424	g/m ²	1485	oz/yd ²	43.8			
Effective pile mass	ISO 8543	g/m ²	1050	oz/yd ²	31.0			
Pile density	ISO 8543	g/cm ³	0.131	lb/in ³	0.0047			
Number of tufts	ISO 1763	/dm ²	870	/yd ²	72741			
Stroll test	ISO 6356	kV						
Vertical resistance	ISO 10965	Ohm						
Horizontal resistance	ISO 10965	Ohm						
Use classification	EN 1307	33 Commercial - heavy use						
Luxury rating	EN 1307	LC 5						
Impact sound reduction ΔL_w	ISO 10140	dB	34					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α_s	0.02	0.05	0.15	0.30	0.53	0.70
Noise reduction	ISO 354	α_w	0.25					
Thermal resistance	ISO 8302	m ² .K/W	0.155					
Flammability	EN 13501-1	Cfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	23315						



Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit www.desso.com

EN-20180329